Technical Data Sheet



1 K WARNEX texture paint Series 74

Product description : Fast-drying 1-pack texture paint with excellent hardness

Binder type : Waterbourne – acrylic

Gloss level : Half matt

Solids content : 52 - 55 % of weight

Recommended dry-film70 μm single coat (orange peel)

thickness : 120 µm double coat (spattered texture)

Theoretical covering rate : $5.5 \text{ m}^2/\text{kg}$ (70 µm) $3.2 \text{ m}^2/\text{kg}$ (120 µm)

Practical average covering

rate : 1,5 m²/kg for loudspeaker cabinets

Density : $1,15 - 1,20 \text{ g/cm}^3$

Viscosity : Delivery viscosity Rheolab 700 - 1400 mPas / D 70 ¹/s

Application viscosity Ready to spray

Application parameters : High pressure spraying with pressure tank or pressure cup

Air pressure
Material pressure
2 - 4 bar
2 - 5 bar

Material hose
Min. 9 mm internal-Ø / max. 6 m length

Nozzle size : 1,5 - 2,0 mm
Cross coats : 1 - 1 ½
Spray distance : 30 - 40 cm

Thinner : De-ionised water (if necessary)

Spraying equipment must be rinsed with water after use

Drying:

Dust-free	Ready for handling	Through-dry	Wärmebeschleunigt	Einbrennen
15 – 20 min	2 – 3 hrs	4 Days	60 min / 60°C Circulated air Flash-off 15 min	-

Depending on: air and object temperature, film thickness, relative humidity and air flow.

Substrate: As a single coat on woods such as MDF, birch ply-wood and many types of plastic. If in

doubt, perform an adhesion test. Metal surfaces may require a Primer.

Various: Because of the fast drying time and to achieve a high spraying speed, a closed system,

such as pressure pot or a double-membrane pump with lid, should be used.

Storage: Protect from frost, heat and direct sun-light

max. 9 months in originally sealed containers

Technical Service:

Warnecke & Böhm GmbH Westerbergstraße 12 83727 Schliersee GERMANY

Notice:

Tel.: +49 8026 9407-0 Fax: +49 8026 20067 www.wb-coatings.de Series 74 2015-03 Page 1 of 1

The above stated information is intended as a guideline and is based on our experience and tests. However, no responsibility, assurance or guarantee are assumed by providing this information.